

Data Sheet		EN AW 3003 – Rolled products		Alumeco A/S		Internal alloy name: 3003		International alloy name: EN AW 3003		Chemical Symbol: EN AW – Al Mn1Cu		DIN-Werkstoff no.: 3.0517		Alloy type: Non heat treatable alloy	
Main usage			Main properties			Important norms and literature									
<ul style="list-style-type: none"> • Facade panels • Covers • Deep-drawn parts • Pre-painted coils/sheets 			<ul style="list-style-type: none"> • Very good atmospheric corrosion resistance • Very good workability • Very good weld ability • Low mechanical properties 			Cold rolled products: EN 485-1: Technical conditions for inspection and delivery EN 485-2: Mechanical properties EN 485-4: Tolerances on dimensions and form cold rolled products Chemical composition: EN 573-3: Chemical composition									
Chemical composition (%) EN 573-3															
Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Other elements							
								Each	together						
0.6	0.7	0.05 – 0.20	1.0 – 1.5	-	-	0.10	0.05	0.05	0.15						
Typical mechanical properties EN 485 - 2															
Thickness range (mm)		Temper		Rm MPa		Rp _{0,2} MPa		A ₅₀ %		Hardness* HB		Bend radius**			
												180°	90°		
0.5 up to 1.5		H14		145 – 185		Min. 125		2		46		2.0t	1.0t		
1.5 up to 3.0		H14		145 – 185		Min. 125		3		46		2.0t	1.0t		
3.0 up to 6.0		H14		145 – 185		Min. 125		4		46		-	2.0t		
** Information values only															
Physical properties															
Density g/cm ³		Solidification range °C		Electrical conductivity %IACS		Thermal conductivity W/m K		Thermal expansion (µm m ⁻¹ K ⁻¹)		Annealing temperature °C		E - modulus (N / mm ²)			
2.73		640 - 655		42		160		23.1		350 - 400		69,500			
Typical Alumeco products with this alloy															
<ul style="list-style-type: none"> • Coils in width of 1000 mm in thicknesses 0,63; 0,75; 0,88; 1,00 mm. • Materials are typically Continuously Cast (CC) materials 															
Properties and information (3 high/good; 2 medium; 1 poor/bad)															
<u>Resistance</u> Corrosion index, general: 3 Marine atm. corr. index: 3 <u>Hot workability</u> Extrusion: 3 Forging: 3 <u>Cold formability</u> Cold formability general: 3 Deep drawing: 2 Bending: 3 Be aware that the formability categorizations depend on the temper of the alloy.			<u>Weldability</u> TIG welding: 3 MIG welding: 3 <u>Solderability</u> 3			<u>Machinability</u> Machinability index: 1 <u>Tips regarding machining</u> Tools for aluminum processing: High-usable cutting speeds, possibly > 2000 m / min.			<u>Anodizing</u> Decorative anodizing surface treatment: 3 (CC cast materials 1) Protective anodizing index: 3 Hard anodizing: 3 Color anodizing: 3 (CC cast materials 1) <u>General information</u> Decorative anodizing cannot be recommended for continuously cast (CC) materials						